



STYCCOBOND F54

High Grab Linoleum Adhesive

PRODUCT DATA

INTRODUCTION

STYCCOBOND F54 is a non-flammable, synthetic rubber emulsion adhesive for installing linoleum. It is designed to provide a high initial grab. It is protected against bio-degradation and is suitable for use over normal underfloor heating installations.

STYCCOBOND F54 can be used for securing a wide range of linoleum floorcoverings.

See the STYCCOBOND Recommended Adhesives Guide for details of specific floorcoverings.



STYCCOBOND F54 has been tested to the standards of the International Maritime Organisation and approved for use in marine floor installations by DNV - Det Norske Veritas.

STYCCOBOND F54 can be applied to STOPGAP smoothing underlayments, structurally sound, smooth, dry subfloors of concrete and sand/cement screed, plywood, flooring grade chipboard and hardboard.

STOPGAP Waterproof Surface Membranes, sound flooring grade asphalt and other non-absorbent surfaces must be skimmed with a minimum of 3mm of the appropriate STOPGAP smoothing underlayment.

For details on other subfloors, contact our Technical Services Department.



FEATURES

- High initial grab
- Non-flammable
- Approved for marine use.

STANDARDS

All aspects of the installation of floorcoverings should be in accordance with the requirements of the relevant British Standard Code of Practice i.e. BS 8203 (Installation of resilient floorcoverings) and supplementary specifications.

PACKAGES

- 15 litre bucket
- 5 litre bucket

TECHNICAL INFORMATION

Colour	Off White
Consistency	Creamy
Coverage Rate (Approx.)	3m ² per litre with 2mm x 6mm trowel
Open Time	Up to 30 minutes depending on temperature, humidity and absorbency of the subfloor

HOW MUCH MATERIAL?

PACK SIZE	TROWEL SIZE	COVERAGE PER UNIT
15 litres	2mm x 6mm	45m ²
5 litres	2mm x 6mm	15m ²

Note: Coverage rates will depend on the condition and absorbency of the subfloor.

SURFACE PREPARATION

Proper subfloor preparation is essential for the correct installation of any floorcovering. Subfloors must be structurally sound, smooth, dry (<75% RH) and free from laitance and any contaminants which will affect adhesion. Use STYCCOCLEAN C140 for removing grease, oil, polish, soap etc. from non-absorbent substrates.

Concrete and sand/cement screeds must be fully cured and any laitance or surface treatments must be removed. The temperature of the floor must be maintained above 10°C throughout the application and drying of the adhesive. Underfloor heating must be off for at least 48 hours before, during and after application.

For detailed information, request the F. Ball Subfloor Preparation Guide.

DAMP SUBFLOORS

The Relative Humidity (RH) of the subfloor can be measured using the F. Ball Digital Hygrometer. Where the RH value is greater than 75% the appropriate STOPGAP Waterproof Surface Membrane should be applied.

SMOOTHING

To ensure a level surface on which to adhere to, uneven and irregular surfaces should be suitably prepared using the appropriate STOPGAP smoothing underlayments.

PRIMING

Highly absorbent subfloors such as sand/cement screeds and plywood etc. may cause rapid drying of the adhesive, thus reducing the open time. Use STOPGAP P131 diluted 4 parts of water and stir until thoroughly dispersed. This should be allowed to dry thoroughly before proceeding with the installation.

Dry and suitably prepared calcium sulphate screeds e.g. anhydrite must be primed with neat STOPGAP P121.

ADHESIVE APPLICATION

Holding the trowel at an angle of 60°, spread the adhesive evenly over an area of subfloor that can be covered whilst the adhesive remains receptive and gives good transfer.

Following the floorcovering manufacturers laying instructions place the floorcovering into the adhesive and press from the centre outwards to exclude any air; then roll from end-to-end and side-to-side using the 68kg flooring roller. 1 to 4 hours later roll again in two directions.

PRECAUTIONS

Surplus adhesive may be removed from the surface of the flooring whilst it is still wet, using a cloth dampened with water. Allow the adhesive to dry overnight before commencing seam welding operations.

TOOLS

STYCCOBOND 2mm x 6mm 'V' notched trowel, F. Ball 68kg flooring roller, Trimming knife.

Tools should be cleaned with warm soapy water while the adhesive is still.

STORAGE

Store between 5°C and 30°C. Protect from frost.

SHELF LIFE

12 months in unopened containers stored under good conditions.

HEALTH AND SAFETY ADVICE

This product is not classified under the Chemicals (Hazard Information and Packaging for Supply) Regulations. A Material Safety Data Sheet is available for professional users on request. These can be found at www.f-ball.co.uk alternatively these can be obtained from the point of purchase or from F. Ball and Co. Ltd. at the address below.

Site conditions vary, to ensure this product is suitable and to confirm this data sheet is current please contact our Technical Services Department.

For further information about F. Ball products or more detailed technical assistance, please contact:



F. Ball and Co. Ltd.

Churnetside Business Park
Station Road, Cheddleton, Leek
Staffordshire ST13 7RS
United Kingdom

Tel: +44 (0) 1538 361633
Fax: +44 (0) 1538 361622
Tech Services Fax: +44 (0) 1538 361567
Email: mail@f-ball.co.uk

www.f-ball.co.uk